


## TECHNICAL DATA PROBOND décor®

PROBOND Decor<sup>®</sup> has been developed to allow the addition of highlights and feature cladding for creative interior decor elements such as feature walls and pylons to internal fitouts. It is also suitable for formwork and signage for all branding solutions.

The special surface finishes of PROBOND Decor<sup>®</sup> allow designers to add creative flair and class that cannot be created using standard coloured panels.

PROBOND Decor® is recommended for internal applications only.



Surface Finish A range of special effects such as mirror finish and brushed textures.

**Clear Protective Film** An easy-peel protective liner protects the face during transit and installation. Clear film is ideal for quick and easy colour and finish identification.



	PROBOND Decor - Properties
Panel Thickness (mm)	3mm
Aluminium Thickness (mm)	0.30mm
Weight (kg/m2)	4.5kg
Sound Absorption	0.05
Sound Attenuation	24
Water Absorption % by Volume	0.01
Thermal Performance R Values	0.008
Core Composition	LDPE
Tensile Strength of Aluminium Layers	39 MPa
Bending Strength	>60MPa
Bending Elastic Modulus	>1.5 x 10 <sup>4</sup> MPa
Penetration Resistance	>5.0kN
Shearing Strength	>20.0MPa
Standard Sizes (mm)	2440mm X 1220mm, 3660mm X 1220mm



PROBOND ARCHITECTURAL T 1300 72 73 74 www.probond.com.au PAGE 1/2 - FEBRUARY 2019



## TECHNICAL DATA PROBOND décor®

Dimensional tolerances	
Panel Thickness (mm)	3mm
Width (mm)	-0 +2 (+/-0.2)
Length (mm)	-0 +3 (+/-0.2)
Diagonal	-0 +5 (+/-0.2)
Thermal Expansion	2.4mm/m @100°C temp difference
Aluminium Thickness	0.30 mm

Surface Properties	
Paint Thickness (microns)	17±1µm
Pencil Hardness	2Н
Toughness of Coating	≤2T
Temperature Resistance	-50°C-80°C
Impact Strength (kg/CM2)	50kg/cm2. No crack
Boiling Water Resistance	Boiling for 2 hours without change
Acid Resistance	Immerse surface with 2%HCL(v/v) for 24H without change
Alkali Resistance	Immerse surface with 2%NaOH(m/m) for 24H without change
Oil Resistance	Immerse surface with 20# engine oil for 24H without change
Solvent Resistance	Clean 100 times with Methyl Ethyl Ketone (MEK) without change
Peel Strength	6 N/mm

## **Recyclability and Recycling Service**

All PROBOND® Architectural Aluminium Composite Panel are fully recyclable.

The aluminium skins and core material can be fully recycled and reused in the production of new materials.

With a commitment to the environment, **PROBOND® Architectural** conducts a complete recycling program and receives Aluminium Composite Panel waste and off-cuts for the purposes of recycling.

## **Environment and Health and Safety**

During the lifecycle of **PROBOND®** Aluminium Composite Panel no substances containing CFC, VOCs are released. All finishes used in the production of **PROBOND®** Aluminium Composite Panel are RoHS compliant and do not contain Lead, Cadmium, Chromium or Mercury.

Published information concerning PROBOND products is based upon research which the company believes to be reliable but such information does not constitute a warranty. Because of the variety of possible uses for PROBOND products and the continuing development of new uses, the purchaser should carefully consider the fitness and performance of the product for each intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product of for incidental or consequential damages.

All specifications subject to change without prior notice.

PAGE 2/2 - FEBRUARY 2019



PROBOND ARCHITECTURAL T 1300 72 73 74 www.probond.com.au